



TECHNICAL BULLETIN

EPOXIBOND EB-260 HIGH STRENGTH, FLEXIBLE EPOXY ADHESIVE

EB-260 is a toughened, high strength, structural epoxy adhesive. This adhesive has an excellent combination of shear and peel strength. It has also excellent impact and vibration resistance and low temperature flexibility. This high performance epoxy adhesive exhibits very good physical, thermal, and electrical insulation properties. It is recommended for bonding engineering thermoplastics, SMC (sheet molding compounds) in aerospace and automotive applications. EB-715 is also recommended for bonding gold club heads.

TYPICAL HANDLING PROPERTIES:

Epoxybond	260-A
Hardener	260-B
Mix ratio by weight, (Resin/Hardener)	100/50
Mix viscosity (25°C), cps	30,000-40,000
Pot Life at 25°C (20 grams), minutes	60-80
Recommended Cure	24hrs/25°C
Alternate Cure	1 hr/65°C

TYPICAL CURED PROPERTIES AFTER RECOMMENDED CURE:

(Tested @ 25°C unless otherwise indicated)

Color	Black/White
Specific Gravity	1.14
Hardness, Shore D	77
Lap Shear Strength to Aluminum, psi	4500
Lap Shear Strength to Aluminum after 7 days, psi	
Stainless Steel	4000
Copper	4500
Brass	4100
T-peel strength to aluminum (5-8mil bondline)	50
Service Temperature range, °C	-55 to 120
Glass Transition Temperature, °C	60
Coefficient of Linear Thermal Expansion, 10 ⁻⁶ /°C	
Below Tg	77
Above Tg	195
Dielectric Strength, Volts/mil	900
Dielectric Constant, 1 kHz	4.28
Dissipation Factor, 1 kHz	0.4
Volume Resistivity, ohm-cm	2x10 ¹⁵

INSTRUCTIONS FOR USE:

1. Mix at room temperature, 100 grams of Part-A with 50 grams of Part-B and vacuum degas.
2. Cure as recommended achieving the desired properties.
3. Typical cured properties were determined using recommended cure schedule. Some difference in properties may occur with the alternate or other cure schedules.

FOR INDUSTRIAL USE ONLY:

These materials are intended for industrial use only, and the practices of good housekeeping, safety and cleanliness should be followed before, during and after use.

PACKAGING OPTIONS:

Available in Pint, Quart, Gallon, and 5-gallon kits.

Also available in 50mL and 400mL dual cartridge systems.

WARNING!

Although the system contains low volatility materials, care should be taken in handling. Adequate ventilation of work place and ovens is essential. These materials may cause injury to the skin following prolonged or repeated contact and dermatitis in susceptible individuals. In case of skin contact, wash thoroughly with soap and water. For eyes, flush immediately with plenty of water for at least 10 minutes and seek medical attention. Refer to Material Safety Data Sheet for additional health and safety information.

SHELF LIFE:

The shelf life of these materials is greater than two years when stored in unopened containers at an average temperature of 25°C.