



FLASHBOND™

UV-8701E

UV CURE EPOXY

TECHNICAL DATA **SEPTEMBER 2019**

Product Description

UV-8701E is a thixotropic, light curing epoxy adhesive that bonds well to a wide variety of substrates including engineered plastics such as Ultem™, Lexan™, and ABS. This product exhibits good surface wetting and adhesion to glass and many plastics. UV-8701 is clear magenta when uncured but turns translucent when cured as a built in cure indicator. This product requires direct light exposure during cure. Because of the variability of different UV/LED light sources, it is suggested that the user test and specify intensity and exposure time. This product will cure in the presence of visible light (400-415nm). Can be cured at 150°C for shadowed areas if necessary.

APPLICATIONS

- Electronics
- Encapsulation
- Sealant

FEATURES

- RoHS & REACH Compliant
- Excellent Chemical Resistance
- High Bond Strength
- Fast UV Cure

SUBSTRATES

- Metals
- Ceramics
- Glass
- Plastics

PACKAGING

- Syringes
- Bulk

TYPICAL PROPERTIES OF UNCURED MATERIAL	
Property	Value
Chemical Class	Cationic Epoxy
Appearance	Magenta
Viscosity, 20 RPM @ 25°C, cps	5,000 to 9,000
Viscosity, 2 RPM @ 25°C, cps	15,000 to 20,000
Specific Gravity	1.14

TYPICAL PROPERTIES OF CURED MATERIAL	
Property	Value
Glass Transition Temperature (Tg), °C	135
Hardness, Shore	D-78
Ultimate Tensile Strength, PSI	5,000
Elongation at Break, %	6
Operating Temperature Range, °C	-55 to 250
Volume Resistivity, Ω-cm	1 x 10 ¹⁴

***All properties given are typical values and are not intended for use in preparing specifications.**

CURE OVERVIEW	
Optimal Wavelength	400-415nm
Optimal Intensity	100-200 mW/cm ²

SHELF LIFE, STORAGE

18 ± 10°C 1 Year DOM

MATERIAL IS LIGHT SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

EPOXYSET MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. EPOXYSET'S LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.