



ISO 9001-2015 Certified

718 Park East Drive, Woonsocket RI 02895, USA

Phone: (401) 726-4500

Email: [info@epoxyset.com](mailto:info@epoxyset.com) ■ Web: [www.epoxysetinc.com](http://www.epoxysetinc.com)

## TECHNICAL BULLETIN

### CTG-87NS

#### HIGH CONDUCTIVITY THERMAL GREASE

CTG-87NS is non-silicone; non-curing, silver filled electrically and thermally conductive grease. It can be used as interfacial contact for electrical and thermal transfer for power devices. CTG-87NS was specially formulated using various size silver flakes to maximize particle contact resulting in an extremely high thermal conductivity. This material will not dry, harden or melt in normal industrial use and provides long term material stability.

#### TYPICAL PROPERTIES:

Color	Silver
Specific Gravity	3.1
Consistency	Smooth Paste
Evaporation, @ 200°C, 24 hrs, %/Wt	0.4
Operating Temperature Range	-55°C to 200°C
Thermal Conductivity, W/m-°K	7.0
Thermal Resistance, °C-in <sup>2</sup> /W	0.005
Dielectric Strength (0.05" gap), Volts/mil	380
Dielectric Constant, 1 kHz	4.0
Dissipation Factor, 1 kHz	0.003
Volume Resistivity, ohm-cm	<0.01

#### FOR INDUSTRIAL USE ONLY:

These materials are intended for industrial use only, and the practices of good housekeeping, safety and cleanliness should be followed before, during and after use.

#### WARNING!

Although the system contains low volatility materials, care should be taken in handling. Adequate ventilation of work place and ovens is essential. In case of skin contact, wash thoroughly with soap and water. For eyes, flush immediately with plenty of water for at least 10 minutes and seek medical attention. Refer to Material Safety Data Sheet for additional health and safety information.

#### SHELF LIFE:

The shelf life of these materials is greater than one year when stored in unopened containers at an average temperature of 25°C.

#### DISCLAIMER:

All data given here is offered as a guide to the use of these materials and not as a guarantee of their performance. The user should evaluate their suitability for own purposes. Properties are typical and should not be used in preparing specifications. Statements are not to be construed as recommendations to infringe any patent.