



718 Park East Drive, Woonsocket, RI 02895 USA
 Phone: +1 (401)-726-4500
 Email: info@epoxyset.com www.epoxyset.com

FLASHBOND™

UV-3607HT

UV/HEAT CURE EPOXY

TECHNICAL DATA **MARCH 2020**

Product Description

UV-3607HT is a 1-component, UV/Thermal cure adhesive & sealant. This material can cure under moderate intensity UV light as well as elevated temperatures for shadowed areas. Its low viscosity is ideal for coating, capillary action, and doming applications.

APPLICATIONS

- Electronics
- Encapsulation
- Sealant

FEATURES

- RoHS & REACH Compliant
- Excellent Chemical Resistance
- High Bond Strength
- Fast UV Cure

SUBSTRATES

- Metals
- Ceramics
- Glass

PACKAGING

- Syringes
- Bulk

TYPICAL PROPERTIES OF UNCURED MATERIAL	
Property	Value
Chemical Class	Cationic Epoxy
Appearance	Clear
Viscosity, 20 RPM @ 25°C, cps	3,000 to 4,000
Specific Gravity	1.12

TYPICAL PROPERTIES OF CURED MATERIAL	
Property	Value
Glass Transition Temperature (Tg), °C	125
Hardness, Shore	D-80
Ultimate Tensile Strength, PSI	5,000
Elongation at Break, %	4-6
Operating Temperature Range, °C	-55 to 200
Volume Resistivity, Ω-cm	1 x 10 ¹⁴

***All properties given are typical values and are not intended for use in preparing specifications.**

CURE OVERVIEW	
Optimal Wavelength, Intensity	315, 365nm 100-300 mW/cm ²
Thermal Cure	30 minutes @ 125°C

SHELF LIFE, STORAGE

23°C ± 5°C 1 Year DOM

MATERIAL IS LIGHT SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

EPOXYSET MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. EPOXYSET'S LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.