



718 Park East Drive, Woonsocket, RI 02895 USA
 Phone: +1 (401)-726-4500
 Email: info@epoxyset.com www.epoxyset.com

FLASHBOND™

UV-3700F

(Formerly BP023701F)

UV CURE EPOXY

TECHNICAL DATA **SEPTEMBER 2019**

Product Description

UV-3700F is a filled, low shrinkage, light curing epoxy adhesive that offers low CTE and high bonds strength. UV-3700F cures to a high Tg, rigid polymer with excellent adhesive to metals, ceramics, and glass. This filled system is excellent for when low viscosity systems are not ideal. Due to the variability of different UV/LED light sources, it is suggested that the user test and specify intensity and exposure time. This product will cure in the presence of visible light (400- 415nm).

APPLICATIONS

- Electronics
- Encapsulation
- Sealant

FEATURES

- RoHS & REACH Compliant
- Excellent Chemical Resistance
- High Bond Strength
- Fast UV Cure

SUBSTRATES

- Metals
- Ceramics
- Glass

PACKAGING

- Syringes
- Bulk

TYPICAL PROPERTIES OF UNCURED MATERIAL	
Property	Value
Chemical Class	Cationic Epoxy
Appearance	Off White
Viscosity, 20 RPM @ 25°C, cps	15,000 to 25,000
Specific Gravity	1.50

TYPICAL PROPERTIES OF CURED MATERIAL	
Property	Value
Glass Transition Temperature (Tg), °C	138
Hardness, Shore	D-80
Ultimate Tensile Strength, PSI	4,000
Elongation at Break, %	1-3
Operating Temperature Range, °C	-55 to 250
Volume Resistivity, Ω-cm	1 x 10 ¹⁴

***All properties given are typical values and are not intended for use in preparing specifications.**

CURE OVERVIEW	
Optimal Wavelength	365, 405nm
Optimal Intensity	100-300 mW/cm ²

SHELF LIFE, STORAGE

23°C± 10°C 1 Year DOM

MATERIAL IS LIGHT SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

EPOXYSET MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. EPOXYSET'S LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.