



718 Park East Drive, Woonsocket, RI 02895 USA  
 Phone: +1 (401)-726-4500  
 Email: info@epoxyset.com www.epoxyset.com

# FLASHBOND™

## UV-8300T

### LIGHT CURABLE EPOXY

#### TECHNICAL DATA

NOVEMBER 2021

#### Product Description

UV-8300T is a filled, thixotropic, light curing epoxy adhesive that offers low CTE and high bonds strength. UV-8300T cures quickly to a high bond strength polymer with excellent adhesive to metals, ceramics, and glass. This epoxy was specifically designed as a dam material for dam & fill encapsulation of chip modules on PCBs and smart cards. This material is solvent free and has high ionic purity. UV-8300T should be used in conjunction with a low viscosity flowable epoxy such as UV-5403S or UV-5400LV for the fill material.

#### APPLICATIONS

- Dam & Fill
- General Bonding
- General Encapsulant

#### FEATURES

- Passes 1000 cycles 85%RH/85°C
- Halogen Free (IEC 61249-2-21)
- High Bond Strength
- RoHS & REACH Compliant

#### SUBSTRATES

- FR4
- Metals
- Glass

#### PACKAGING

- Syringes
- Bulk

#### TYPICAL PROPERTIES OF UNCURED MATERIAL

Property	Value
Chemical Class	Cationic Epoxy
Color	Natural White
Viscosity, 25°C, cPs	120,000 - 180,000
Density, g/mL	1.40
Thixotropic Index	4.5 - 5.0

#### TYPICAL PROPERTIES OF CURED MATERIAL

Property	Value
Glass Transition Temperature (Tg), °C	72
Hardness, Shore	D-78
Ultimate Tensile Strength, PSI	5,000
Elongation at Break, %	1-3
Operating Temperature Range, °C	-55 to 150
Volume Resistivity, Ω-cm	1 x 10 <sup>14</sup>

**\*All properties given are typical values and are not intended for use in preparing specifications.**

#### CURE OVERVIEW

Optimal Wavelength	UV/LED 310nm-365nm
Optimal Intensity	100-300 mW/cm <sup>2</sup>

\*Cure time is dependent on light intensity and lamp type. Test specimens were cured for 30 seconds at 150 mW/cm<sup>2</sup> under a 365nm LED light.

#### SHIPPING, SHELF LIFE, STORAGE

STORE AT 2-10°C, SHELF LIFE: 6 MONTHS

MATERIAL IS LIGHT & HEAT SENSITIVE. CONSULT SDS FOR SAFE HANDLING RECOMMENDATIONS.

#### THIS MATERIAL IS SOLD FOR INDUSTRIAL USE ONLY

**EPOXYSET MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. EPOXYSET'S LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.**